





## Clairbook White & Ivory

Detailed data sheets upon request.

Bulk cm <sup>3</sup> /g	Roughness ml/min	Thickness $\mu$ m					Application
		65gsm	70gsm	80gsm	90gsm	100gsm	
1.3	150	-	-	105	117	-	Book Printing  
1.5	240	-	105	120	135	-	
1.8	650	117	126	144	162	-	
2.0	850	-	-	160	-	200	

## Clairjet® 400



Substance gsm	Brightness CIE	Opacity %	Thickness $\mu$ m	Bendtsen Roughness ml/min	Gloss %	Application
60	168	93	82	150	<10	Transactional  
70	168	93,5	94	150	<10	
80	168	94,5	109	150	<10	
90	168	96	122	150	<10	

## Everjet 400 100% Recycled



Data for 80 gsm. Also available from 70 to 200 gsm.

Grade	Brightness CIE	Opacity %	Thickness $\mu$ m	Bendtsen Roughness ml/min	Gloss %	Application
Plus	95	97	96	150	<10	Transactional   
Performance	120	96	96	150	<10	
Premium	145	95	96	150	<10	
Prestige	160	93	96	150	<10	



## Clairjet® 1200

Substance gsm	Brightness CIE	Opacity %	Thickness $\mu$ m	Bekk Smoothness s	Gloss %	Application
80	162	95	92	80	<10	Transpromotional & Direct Marketing  
90	162	97	104	80	<10	
120	162	99	138	80	<10	
160	162	>99	184	80	<10	

## Clairjet® 1000 ICY® Original & Bright

Substance gsm	Brightness CIE Original / Bright		Opacity %	Thickness $\mu$ m	Bekk Smoothness s	Gloss %	Application
80	152	162	93	85	180	22	Transpromotional & Direct Marketing  
90	152	162	94,5	95	180	22	
120	152	162	96	127	180	22	
160	152	162	98	168	180	22	

## Clairjet® 1300 ICY® Original & Bright

Substance gsm	Brightness CIE Original / Bright		Opacity %	Thickness $\mu$ m	Bekk Smoothness s	Gloss %	Application
80	152	162	94	85	180	20	Transpromotional & Direct Marketing  
90	152	162	95,5	95	180	20	
120	152	162	97	127	180	20	
160	152	162	99	168	180	20	

Clairjet range has been tested and is daily used on the printing presses of all leading manufacturers.